CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

An ISO 9001:2008 Certified Company

JAS-ANZ BSCIC ISO 9001 REGISTERED

Job No.: CTCE/BBMP/W.No.06/HSN/WMM/Gradation/2013-14 17.12.2013

GRADATION FOR WMM

MORTH TABLE-400-11

Client : **Asst. Executive Engineer,** Byatarayanapura Sub Division, BBMP, Bangalore.

Agency : **Mr. H.S. Nataraj,** Contractor,Bangalore.

Name of Work : Providing and asphalting to road at Shabarinagar in Ward No.06 Byatarayanapura Sub Division, BBMP, Bangalore.

Reference : EE/BTP/BBMP/E-TND/460/2012-13 Dated: 20.03.2013

Date of Testing : 17.12.2013

Material : WMM

Sample Location : WMM Mix Plant Oven Dry Wt (gm): 8885

Is Sieve Size in mm	Weight Retained (gm)	Cumulative Weight Retained (gm)	Cumulative % of Retained	Cumulative % of Passing	Spec.Limits
53	0	0	0	100	100
45	295	295	3.3	96.7	95-100
22.4	2900	3195	36.0	64.0	60-80
11.2	1525	4720	53.1	46.9	40-60
4.75	1150	5870	66.1	33.9	25-40
2.36	985	6855	77.2	22.8	15-30
0.600	880	7735	87.1	12.9	8-22
0.075	800	8535	96.1	3.9	0-8

Note:

1. The report shall not be reproduced, except in full, without the written approval of the laboratory.
2. The results indicated above are based on the tests carried out on the samples received in the laboratory.
3. Any Query regarding the report must be reported within 30 days from the date of testing.

Civil-Tech Consultants & Engineers Bangalore

M/s. Civil-Tech Consultants & Engineers
23/14, 7th Cross, 3rd Stage,
4th Block, Shakthiganapathinagara,
Basaveshwaranagar,
Bangalore-560079.

CIVIL-TECH CONSULTANTS AND ENGINEERS

Building & Highway Material Testing Laboratory

An ISO 9001:2008 Certified Company

JAS-ANZ BSCIC ISO 9001 REGISTERED

Job No.: CTCE/BBMP/W.No.06/HSN/SDBC/Bitumen/2013-14 23.12.2013

BITUMEN CONTENT AND GRADATION DETERMINATION OF SEMI DENSE BITUMINOUS CONCRETE MIX

As per IS2386 and IRC:SP:11-1984

CLIENT	**Asst. Executive Engineer,** Byatarayanapura Sub Division, BBMP, Bangalore.
AGENCY	**Mr. H.S. Nataraj,** Contractor,Bangalore.
NAME OF THE WORK	Providing and asphalting to road at Shabarinagar in Ward No.06 Byatarayanapura Sub Division, BBMP, Bangalore.
REFERENCE	EE/BTP/BBMP/E-TND/460/2012-13 Dated: 20.03.2013
SAMPLE I/D	Roads in Shabarinagar in Ward No.06, BBMP, Bangalore.
DATE OF TESTING	23.12.2013

BITUMEN CONTENT DETERMINATION

Description	Trail 1	Trail 2
1. Weight of Mixture before Test, g	500	500
2. Weight of Mixture after Test, g	475.5	474.5
3. Weight of Asphalt and Mineral matter Extracted,	-	-
4. Weight of Mineral Matter, g.	-	-
5. Weight of Ash, g		
6. Weight of Bitumen Extracted, g. (corrected)	24.5	25.50
7. Bitumen content in %	4.90	5.10
8. Average	**5.00**	

GRADATION AFTER EXTRACTION

SIEVE SIZE	Trail 1				JOBMIX
mm	Weight Retained, gm	% Retained	%Cummulative Retained	% Passing	Gradation
13.2	0	0	0	100	100
9.5	34.25	7.20	7.20	92.80	90-100
4.75	255.5	53.73	60.94	39.06	35-51
2.36	43.35	9.12	70.05	29.95	24-39
1.18	39.65	8.34	78.39	21.61	15-30
0.3	42.32	8.90	87.29	12.71	9-19
0.075	39.22	8.25	95.54	4.46	3-8

SIEVE SIZE	Trail 2				JOBMIX
mm	Weight Retained, gm	% Retained	%Cummulative Retained	% Passing	Gradation
13.2	0	0	0	100	100
9.5	36.32	7.26	7.26	92.74	90-100
4.75	259.3	51.86	59.12	40.88	35-51
2.36	33.32	6.66	65.79	34.21	24-39
1.18	45.56	9.11	74.90	25.10	15-30
0.3	48.25	9.65	84.55	15.45	9-19
0.075	56.36	11.27	95.82	4.18	3-8

Note:

- This test report should not be reproduced except in full, without written approval of the laboratory
- The results indicated above are based on the tests carried out on the samples received in the laboratory
- Any Query regarding the report must be reported within 30 days from the date of testing.

M/s. Civil-Tech Consultants & Engineers

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthi Ganapathi Nagara, Basaveshwaranagara, Bangalore-79
Tele fax : 23223227, Cell : 93428 39190, Website : www.civiltechconsultants.com
e-mail : vishwanath.ia@civiltechconsultants.com / info@civiltechconsultants.com

#23/14, 7th Cross, 3rd Stage, 4th Block, Shakthiganapathinagara, Basaveshwaranagar, Bangalore-560079,